## Cotton Association Of India

## COTTON TESTING & RESERACH LABORATORY

210, Toral Complex, 2nd Floor, Jawahar Road, Rajkot-360 001, Tel. No. 3047537/38, Fax-2225256

H.O.: Cotton Exchange Bldg., 2<sup>nd</sup> Floor, Opp. Cotton Green Railway St., Cotton Green.

Mumbai- 400 033. Tel: +022-65186830

**Fiber Test Report No** 

1578

Date: 07/11/2011

Samples of cotton submitted by

Rajkot

				Najkot											
SAMPLE DETAILS FURNISHED BY THE PARTY						HVI- (HVI Mode Test Results)									
25								•		3450		CC	LOUF	2	
Lab	Station	Variety	Lot No.	Press Running	SB	UHML	ML	UI	Tenacity at	ELG	MIC	Rd	+b	CG	SFI
Ref No.		C		No.	No.	(mm)			3.2mm (g.tex)	%					
11/10832	-	-	-	Comber Noil K	-	19.4	14.9	76.9	14.1	6.3	3.7	75.3	9.4	31-3	18.9
11/10833	-	_	, . <b>-</b>	Comber Noil W	-	20.2	15.1	74.6	17.5	6.4	2.9	78.4	10.8	12-1	21.2

SAMPLE D	ETAILS F	URNISH	ED BY T	HE PARTY-Sam	ple Testeo	d on Trasl	h Sepera	tor
Lab	Station	Variety	Lot No.	Press Running	S.B.	Lint %	Trash	Cage
Ref No.				No.	NO.		%	Loss %
11/10832	-	-	-	Comber Noil K	-	99.2	0.48	0.3
11/10833	-	-	-	Comber Noil W	-	98.9	0.52	0.6
		<i>(</i>						$C^{\circ}$

Tested :-

RH 65± 2 % and Temp 27 ± 2° c

NOTES:-

1 Samples are not drawn by the Laboratory

2 The test results relate only to the item tested.

3 This report shall not be used for litigation or publicity.

4 This report shall not be reproduced in part/ full without the written permission of the Laboratory.

Lab Tech.