



QUALITY, QUANTITY WEIGHT AND LOADING SUPERVISION CERTIFICATE

REF: IN/AHD/AGR/201111754/1
REF.No.F530101-00067

SP/DSP

DATE: 27/09/2011

Consignment designated as :

Commodity : Indian Raw Cotton Shankar-6 (Type: V11/41/N28P) Origin: India,
Crop year: 2010-11 Ginning: Ginned Staple Length: 28+ mm, Micronaire: 3.5-4.9
NCL, Strength: 28 GPT grams/tex
Quantity : 320 Bales
Shipper : V P Udyog Ltd
4, Synagogue Street, 10th Floor,
Room 1004, Kolkata, 700001, India.
Buyer :
Contract No. : VPL/CN/10072, Dated:01/08/2011
B/L No. : DMCQAMD0005789, Dated:27/09/2011
L/C NO : 1700-174 11/3923, Dated:22/08/2011

In pursuance of an order received from [redacted] requesting us to carry out the instructions summarized as under: -

- 10 % sampling
- 10% HVI testing
- 100% Bale by bale / Lorry weighment Supervision
- Stuffing Supervision

We report as follows:

SAMPLING:

Between 14/09/2011 to 18/09/2011 the inspector of SGS India Private Ltd, Ahmedabad proceeded and sampled from 10% of the bales selected at random per lot at supplier's Gin, Shekhar & Amreli in Gujarat.

ANALYSIS:

Sample drawn during inspection was tested in our in-house laboratory and the results obtained are as under: (Samples were tested on HVI Machine on HVI mode with the protocol of ASTM D 5867-05).

Note:- HVI testing details as per enclosed annexure-I (Total Pages 02 nos.)

- # The staple length of cotton samples was verified to arrive at a comparable basis to the inch reading.
- # Samples are tested at 27±2 deg. C.
- # Samples were conditioned during 24 hrs at 65±2% relative Humidity.
- # Part of the sample was loosed to perform Micronaire Testing.
- # Results indicate are average results.


ANNEXURE-I

REF : IN/AHD/AGR/20111754/1
COPD NO.:F530101-00067

DATE :27/09/2011

CERTIFICATE NO.110927013D.

Sr. No.	LOT NO. (Declared)	PR NO. (Declared)	NO. OF BALES	SELECTED BALE NO.	Elongation	Fiber Colour Grade		
						Rd	Yellowness	Colour Grade
1	*	10001-10100	100	7	6.7	74.7	10.0	32.-1
				17	6.5	76.1	9.8	21.-4
				27	6.5	76.7	8.9	31.-3
				37	6.6	75.8	10.1	22.-2
				47	6.6	75.7	10.0	22.-2
				57	6.5	73.5	9.9	32.-1
				67	6.5	76.8	9.9	21.-3
				77	6.4	76.4	10.2	22.-1
				87	6.4	76.9	9.7	21.-3
				97	6.5	76.8	9.5	21.-4
2	28	2701-2800	100	4	6.3	74.7	9.9	32.-1
				15	6.3	75.6	9.8	21.-4
				26	6.4	76.5	9.8	21.-3
				33	6.3	75.6	9.7	21.-4
				47	6.4	75.7	9.4	31.-3
				54	6.3	74.6	10.0	32.-1
				63	6.3	73.8	9.0	31.-4
				79	6.3	75.5	9.9	22.-2
				82	6.1	75.9	10.1	22.-1
				98	6.4	75.1	9.9	22.-2
3	27	2601-2700	100	8	6.3	74.8	9.4	31.-3
				19	6.4	76.4	10.0	21.-3
				25	6.4	74.8	10.3	22.-2
				36	6.5	77.9	10.8	12.-1
				44	6.3	77.1	10.5	12.-2
				58	6.3	76.4	10.3	22.-1
				66	6.3	77.9	10.4	12.-2
				73	6.3	76.2	10.4	22.-1
				85	6.4	77.4	10.1	11.-4
				92	6.5	74.7	9.6	31.-3
4	26	2501-2600	20	6	6.3	75.2	10.4	22.-2
				17	6.3	76.5	10.2	22.-1



ANNEXURE-I


REF : IN/AHD/AGR/20111754/1
COPD NO.:F530101-00067

DATE :27/09/2011

CERTIFICATE NO.110927013D.

Sr. No.	Lot No.	PR No.	No.of Bales	Selected Bale No.	Fiber Fineness (MIC)	Upper Half Mean Length	Fibre Strength (g/tex) 1/8 inch	Short Fiber Index (%)	Uniformity Index (%)
1	*	10001-10100	100	7	4.15	29.72	28.8	7.5	83.1
				17	3.87	28.35	30.5	9.1	81.6
				27	3.52	29.45	29.2	7.7	82.2
				37	3.81	29.68	29.8	7.5	83.0
				47	3.53	29.79	29.5	9.1	80.5
				57	3.71	28.51	29.4	8.7	82.2
				67	3.80	29.25	28.8	8.8	81.0
				77	3.55	29.09	28.4	8.2	82.5
				87	3.70	28.14	27.8	8.4	82.1
				97	3.67	28.34	27.5	8.9	82.0
2	28	2701-2800	100	4	3.59	27.02	28.4	10.6	80.6
				15	3.66	28.93	28.2	7.7	83.5
				26	4.06	29.82	28.5	8.6	80.7
				33	3.98	28.52	27.8	7.2	84.6
				47	3.63	29.33	28.6	8.8	81.4
				54	3.59	29.61	28.1	8.7	81.3
				63	3.73	28.73	30.4	8.7	81.9
				79	3.32	27.56	27.2	9.5	81.6
				82	3.64	26.70	26.8	10.3	81.1
				98	3.47	28.60	27.3	10.0	80.4
3	27	2601-2700	100	8	3.80	27.49	26.8	9.7	81.3
				19	4.10	28.69	27.5	11.0	79.1
				25	3.56	28.42	28.2	9.7	80.9
				36	3.66	29.49	29.1	9.2	80.4
				44	3.78	28.32	29.1	9.0	81.2
				58	3.31	28.84	27.5	8.9	81.6
				66	3.42	27.42	27.1	12.4	78.9
				73	3.30	27.50	27.8	10.6	80.4
				85	3.58	29.21	29.5	8.7	81.7
				92	3.81	29.75	29.6	7.3	83.3
4	26	2501-2600	20	6	3.50	28.17	29.2	9.1	82.1
				17	3.67	27.69	29.1	8.8	82.3

For SGS INDIA PRIVATE LIMITED



**ANNEXURE-II
SUMMARY OF WEIGHT**

Certificate No. : 110927013D, Dated:27/09/2011
 Shipper : V P UDYOG LTD, KOLKATA
 File No. : IN/AHD/AGR/20111754/1
 Copd No. : F530101-00067
 No. of Bales : 320 BALES

100% BALE BY BALE WEIGHMENT


Sr. No.	Lot No.	Station	P. R. No. (Declared)	No. of Bales	Gross Weight KGS	Tare Weight KGS	Nett Weight KGS
1	*	SHEKHPAR	10001-10100	100	16230.00	50	16180.00
			TOTAL	100	16230.00	50	16180.00

100% LORRY WEIGHMENT

Sr. No.	Station	Truck No.	Lot No.	P R Nos.	No. of Bales	Gross Weight of Truck(Kgs)	Tare Weight of Trucks- (Kgs)	Gross Weight of Bales- (Kgs)	Tare Weight of Bales- (Kgs) Declared	Net Weight of Bales- (Kgs)
1	AMRELI	GJ 1 BY 6762	27	2601-2700	100	29340	10225	19115	48	19067
			26	2501-2600	20					
2	AMRELI	GJ 1 BV 3233	28	2701-2800	100	24890	8930	15960	40	15920
				TOTAL	220	54230	19155	35075	88	34987

TOTAL WEIGHT

Total Bales	Gross Weight of Bales- (Kgs)	Tare Weight of Bales- (Kgs) Declared	Net Weight of Bales- (Kgs)
320	51305.00	138	51167


SGS INDIA PRIVATE LTD. AHMEDABAD

For SGS INDIA PRIVATE LTD





COTTON WEIGHT LIST

Certificate No. : 110927013D, Dated:27/09/2011
 Shipper : V P UDYOG LTD, KOLKATA
 File No. : IN/AHD/AGR/20111754/1
 Copd No. : F530101-00067

Raw Cotton Bales	100	Station	SHEKHPAR
Lot No.	*	P R Nos.	10001-10100


No.	Gross Kgs.	No.	Gross Kgs.	No.	Gross Kgs.	No.	Gross Kgs.	No.	Gross Kgs.
1	168.500	11	172.500	21	162.500	31	153.000	41	172.500
2	162.500	12	158.000	22	162.000	32	164.000	42	160.500
3	159.500	13	161.500	23	153.000	33	108.000	43	165.000
4	157.000	14	159.500	24	162.500	34	138.000	44	138.500
5	162.000	15	159.000	25	168.500	35	162.000	45	168.500
6	156.000	16	163.000	26	161.000	36	151.000	46	160.000
7	153.000	17	164.000	27	158.500	37	164.500	47	177.500
8	149.500	18	157.000	28	155.500	38	163.000	48	161.000
9	163.500	19	164.500	29	167.000	39	167.000	49	166.000
10	165.000	20	169.500	30	171.000	40	167.000	50	168.000
Total	1596.500		1628.500		1621.500		1537.500		1637.500

al gro	Gross Kgs.	No.	Gross Kgs.	No.	Gross Kgs.	No.	Gross Kgs.	No.	Gross Kgs.
51	173.500	61	160.000	71	171.500	81	170.500	91	165.000
52	174.500	62	163.500	72	174.500	82	174.500	92	163.000
53	158.500	63	165.500	73	158.000	83	164.500	93	158.500
54	168.500	64	164.500	74	150.500	84	153.500	94	171.000
55	163.000	65	161.000	75	170.000	85	166.000	95	168.000
56	168.000	66	159.500	76	163.000	86	153.500	96	169.000
57	165.500	67	155.000	77	167.500	87	155.000	97	166.500
58	160.000	68	162.500	78	160.000	88	165.000	98	162.500
59	166.500	69	160.000	79	158.500	89	174.000	99	162.500
60	163.000	70	170.000	80	164.000	90	163.000	100	163.000
Total	1661.000		1621.500		1637.500		1639.500		1649.000

100 Bales Gross Weight	16230.000 Kgs.
100 Bales Tare Weight	50.000 Kgs.
100 Bales Net Weight	16180.000 Kgs.


Weather	Sunny
Remark	Declared tare wt. 0.500 Kgs./bale

For SGS INDIA PRIVATE LTD



10% SAMPLING & TESTING
File No. IN/AHD/AGR/20111533/1
CLIENT: V P UDYOG LTD, KOLKATA.
COMMODITY: INDIAN RAW COTTON
PROTOCOL: ASTM(HVI) D 2812-07, ASTM D 5867-05

Sr. No.	P.R.No.	No.of bales	Selected bale No.	Elongation	Fiber Colour Grade			Fiber Fineness (MIC)	Upper Half Mean Length	Fibre Strength (g/tex)	Short Fiber Index	Uniformity Index (%)
					Rd	Yellowne ss	Colour Grade					
1	2701-2800	100	4	6.3	74.7	9.9	32.-1	3.59	27.02	28.4	10.6	80.6
			15	6.3	75.6	9.8	21.-4	3.66	28.93	28.2	7.7	83.5
			26	6.4	76.5	9.8	21.-3	4.06	29.82	28.5	8.6	80.7
			33	6.3	75.6	9.7	21.-4	3.98	28.52	27.8	7.2	84.6
			47	6.4	75.7	9.4	31.-3	3.63	29.33	28.6	8.8	81.4
			54	6.3	74.6	10.0	32.-1	3.59	29.61	28.1	8.7	81.3
			63	6.3	73.8	9.0	31.-4	3.73	28.73	30.4	8.7	81.9
			79	6.3	75.5	9.9	22.-2	3.32	27.56	27.2	9.5	81.6
			82	6.1	75.9	10.1	22.-1	3.64	26.70	26.8	10.3	81.1
			98	6.4	75.1	9.9	22.-2	3.47	28.60	27.3	10.0	80.4
2	2601-2700	100	8	6.3	74.8	9.4	31.-3	3.80	27.49	26.8	9.7	81.3
			19	6.4	76.4	10.0	21.-3	4.10	28.69	27.5	11.0	79.1
			25	6.4	74.8	10.3	22.-2	3.56	28.42	28.2	9.7	80.9
			36	6.5	77.9	10.8	12.-1	3.66	29.49	29.1	9.2	80.4
			44	6.3	77.1	10.5	12.-2	3.78	28.32	29.1	9.0	81.2
			58	6.3	76.4	10.3	22.-1	3.31	28.84	27.5	8.9	81.6
			66	6.3	77.9	10.4	12.-2	3.42	27.42	27.1	12.4	78.9
			73	6.3	76.2	10.4	22.-1	3.30	27.50	27.8	10.6	80.4
			85	6.4	77.4	10.1	11.-4	3.58	29.21	29.5	8.7	81.7
			92	6.5	74.7	9.6	31.-3	3.81	29.75	29.6	7.3	83.3
3	2501-2600	20	6	6.3	75.2	10.4	22.-2	3.50	28.17	29.2	9.1	82.1
			17	6.3	76.5	10.2	22.-1	3.67	27.69	29.1	8.8	82.3



For SGS India Private Ltd



10% SAMPLING & TESTING
File No. IN/AHD/AGR/20111533/1
CLIENT: V P UDYOG LTD, KOLKATA.
COMMODITY: INDIAN RAW COTTON
PROTOCOL: ASTM(HVI) D 2812-07, ASTM D 5867-05

Sr. No.	P.R.No.	No.of bales	Selected bale No.	Elongation	Fiber Colour Grade			Fiber Fineness (MIC)	Upper Half Mean Length	Fibre Strength (g/tex)	Short Fiber Index	Uniformity Index (%)
					Rd	Yellowne ss	Colour Grade					
1	10001-10100	100	7	6.7	74.7	10.0	32.-1	4.15	29.72	28.8	7.5	83.1
			17	6.5	76.1	9.8	21.-4	3.87	28.35	30.5	9.1	81.6
			27	6.5	76.7	8.9	31.-3	3.52	29.45	29.2	7.7	82.2
			37	6.6	75.8	10.1	22.-2	3.81	29.68	29.8	7.5	83.0
			47	6.6	75.7	10.0	22.-2	3.53	29.79	29.5	9.1	80.5
			57	6.5	73.5	9.9	32.-1	3.71	28.51	29.4	8.7	82.2
			67	6.5	76.8	9.9	21.-3	3.80	29.25	28.8	8.8	81.0
			77	6.4	76.4	10.2	22.-1	3.55	29.09	28.4	8.2	82.5
			87	6.4	76.9	9.7	21.-3	3.70	28.14	27.8	8.4	82.1
			97	6.5	76.8	9.5	21.-4	3.67	28.34	27.5	8.9	82.0

For SGS India Private Ltd

